



HUAWEI TECHNIAL TEXTILE

Technical Sheet

Inflatable Fabric	Product Code					
Total Weight	DIN EN ISO 2286-2 ASTM D-751.10	450g/m2 13.2oz/sq. yd	510g/m2 15oz/sq. yd	610g/m2 18oz/sq. yd	610g/m2 18oz/sq. yd	650g/m2 19oz/sq. yd
Yarn	Denier	1000x1000D	1000x1000D	1000x1000D	1000x1300D	1000x1000D
Yarn Count	Per Inch	20x20	20x20	20x20	18x16	20x20
Tensile Strength	DIN EN ISO 1421/V1	2200/2100	2300/2200	2500/2400	2500/2500	2600/2500
Warp/Weft	ASTM D-751 B	N/50mm	N/50mm	N/50mm	N/50mm	N/50mm
Tear Strength	DIN 53363	240/230	260/250	280/270	280/280	300/300
Warp/Weft	ASTM D-751 (8 " x 10 ") Specimen	N	N	N	N	N
Adhesion	ASTM D-751 RF Weld	95N/50mm	95N/50mm	95N/50mm	95N/50mm	95N/50mm
Temperature resistance	DIN EN 1876-1 ASTM D-2136	(-40° C/+70° C.	(-40° C/+70° C.	(-40° C/+70° C.	(-40° C/+70° C.	(-40° C/+70° C.
Fire behaviour	ISO 3795	B2	B2	B2	B2	B2
Environmental Protective	EU	CPSIA	CPSIA	CPSIA	CPSIA	CPSIA
Surface Treatment	Acrylic/PVDF	NA	NA	NA	NA	Acrylic
Weather Protection		UV	UV	UV	UV	UV
Special Property						
Available Width	Meter	1-3.2m	1-3.2m	1-3.2m	1-3.2m	1-3.2m

Leading China PVC Fabric Producer
www.chinatarps.com Manager@chinatarps.com 0086-13757342702