



HUAWEI TECHNIAL TEXTILE

Technical Sheet

Mesh/ Screen	Product Code									
Total Weight	DIN EN ISO 2286-2 ASTM D-751.10	130g/m ² 3.8oz/sq. yd	130g/m ² 3.8oz/sq. yd	270g/m ² 8oz/sq. yd	300g/m ² 9oz/sq. yd	350g/m ² 10.2oz/sq. yd	350g/m ² 10.2oz/sq. yd	350g/m ² 10.2oz/sq. yd	400g/m ² 11.8oz/sq. yd	
Yarn	Denier	250x250	500x500	1000x1000D	1000x1000D	1000x1000D	1000x1000D	1000x1000D	1000x1000D	
Yarn Count	Per Inch	22x19	12x12	9x9	12x12	14x14	17x12		8x8	
Tensile Strength	DIN EN ISO 1421/V1	800/700	100/800	1300/1200	1500/1300	1800/1600	2000/1800		2000/1800	
Warp/Weft	ASTM D-751 B	N/50mm	N/50mm	N/50mm	N/50mm	N/50mm	N/50mm		N/50mm	
Tear Strength	DIN 53363	150/130	180/160	180/160	200/180	250/230	400/380		350/320	
Warp/Weft	ASTM D-751 (8 " x 10 ") Specimen	N	N	N	N	N	N		N	
Adhesion	ASTM D-751 RF Weld	80N/50mm	80N/50mm	80N/50mm	80N/50mm	80N/50mm	80N/50mm		80N/50mm	
Temperature resistance	DIN EN 1876-1 ASTM D-2136	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C		-40° C/+70° C	
Fire behaviour	ISO 3795	B2	B2	B2	B2	B2	B2		B2	
Environmental Protective	EU	REACH								
Surface Treatment	Acrylic/PVDF									
Weather Protection		UV	UV	UV	UV	UV	UV		UV	
Special Property										
Available Width	Meter	1-3.2m	1-3.2m	1-3.2m	1-3.2m	1-3.2m	1-3.2m		1-3.2m	

Leading China PVC Fabric Producer
www.chinatarps.com Manager@chinatarps.com 0086-13757342702