



HUAWEI TECHNIAL TEXTILE

Technical Sheet

Ready Made TARPS	Product Code	Any Size	Any Size	Any Size	Any Size	Any Size	Any Size	Any Size
Size		Any Size	Any Size	Any Size	Any Size	Any Size	Any Size	Any Size
Application		General Cover	General Cover	General Cover	General Cover	Lumber Tarp/ Steel Tarp/ General Tarp	Lumber Tarp/ Steel Tarp/ General Tarp	General Cover
Total Weight	DIN EN ISO 2286-2 ASTM D-751.10	400g/m2 11.8oz/sq. yd	450g/m2 13.2oz/sq. yd	510g/m2 15oz/sq. yd	550g/m2 16oz/sq. yd	610g/m2 18oz/sq. yd	610g/m2 18oz/sq. yd	650g/m2 19oz/sq. yd
Yarn	Denier	1000x1000D	1000x1000D	1000x1000D	1000x1000D	1000x1000D	1000x1300D	1000x1000D
Yarn Count	Per Inch	18x18	20x20	20x20	20x20	20x20	18x16	20x20
Tensile Strength Warp/Weft	DIN EN ISO 1421/V1 ASTM D-751 B	2200/2100 N/50mm	2200/2100 N/50mm	2300/2200 N/50mm	2400/2300 N/50mm	2500/2400 N/50mm	2500/2500 N/50mm	2600/2500 N/50mm
Tear Strength Warp/Weft	DIN 53363 ASTM D-751 (8 " x 10 ") Specimen	240/230 N	240/230 N	260/250 N	270/260 N	280/270 N	280/280 N	300/300 N
Adhesion	ASTM D-751 RF Weld	N/50mm	N/50mm	N/50mm	N/50mm	N/50mm	N/50mm	N/50mm
Temperature resistance	DIN EN 1876-1 ASTM D-2136	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C
Fire behaviour	ISO 3795	B2	B2	B2	B2	B2	B2	B2
Environmental Protective	EU	REACH						
Surface Treatment	Acrylic/PVDF							
Weather Protection								
Special Property								

Leading China PVC Fabric Producer
www.chinatarps.com Manager@chinatarps.com 0086-13757342702