



HUAWEI TECHNIAL TEXTILE

Technical Sheet

Truck Tarp/ General Cover	Product Code							
Total Weight	DIN EN ISO 2286-2 ASTM D-751.10	400g/m2 11.8oz/sq. yd	450g/m2 13.2oz/sq. yd	510g/m2 15oz/sq. yd	550g/m2 16oz/sq. yd	610g/m2 18oz/sq. yd	610g/m2 18oz/sq. yd	650g/m2 19oz/sq. yd
Yarn	Denier	1000x1000D	1000x1000D	1000x1000D	1000x1000D	1000x1000D	1000x1300D	1000x1000D
Yarn Count	Per Inch	18x18	20x20	20x20	20x20	20x20	18x16	20x20
Tensile Strength Warp/Weft	DIN EN ISO 1421/V1 ASTM D-751 B	2200/2100 N/50mm	2200/2100 N/50mm	2300/2200 N/50mm	2400/2300 N/50mm	2500/2400 N/50mm	2500/2500 N/50mm	2600/2500 N/50mm
Tear Strength Warp/Weft	DIN 53363 ASTM D-751 (8 " x 10 ") Specimen	240/230 N	240/230 N	260/250 N	270/260 N	280/270 N	280/280 N	300/300 N
Adhesion	ASTM D-751 RF Weld	95N/50mm	95N/50mm	95N/50mm	95N/50mm	95N/50mm	95N/50mm	95N/50mm
Temperature resistance	DIN EN 1876-1 ASTM D-2136	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C
Fire behaviour	ISO 3795	B2	B2	B2	B2	B2	B2	B2
Environmental Protective	EU	REACH						
Surface Treatment	Acrylic/PVDF							
Weather Protection								
Special Property								
Available Width	Meter	1-3.2m	1-3.2m	1-3.2m	1-3.2m	1-3.2m	1-3.2m	1-3.2m

Leading China PVC Fabric Producer
www.chinatarps.com Manager@chinatarps.com 0086-13757342702