



## HUAWEI TECHNIAL TEXTILE

### Tents Fabric

Tents Fabric	Product Code									
<b>Total Weight</b>	DIN EN ISO 2286-2 ASTM D-751. 10	400g/m2 11.8oz/sq. yd	440g/m2 13oz/sq. yd	545g/m2 16oz/sq. yd	510g/m2 15oz/sq. yd	650g/m2 19oz/sq. yd	750g/m2 22oz/sq. yd	850g/m2 25oz/sq. yd	950g/m2 28oz/sq. yd	
<b>Yarn</b>	Denier	250x250D	1000x1000D	1000x1000D	1000x1000D	1000x1000D	1000x1000D	1000x1000D	1000x1000D	1000x1000D
<b>Yarn Count</b>	Per Inch	22x19	9x9	9x9	20x20	23x23	23x23	23x23	30x30	
<b>Tensile Strength</b>	DIN EN ISO 1421/V1	1300/1100	1500/1300	1600/1500	2200/2100	2800/2700	2900/2800	3000/2800	3800/3500	
<b>Warp/Weft</b>	ASTM D-751 B	N/50mm	N/50mm	N/50mm	N/50mm	N/50mm	N/50mm	N/50mm	N/50mm	N/50mm
<b>Tear Strength</b>	DIN 53363	150/120	170/150	180/160	230/220	290/280	300/290	310/300	450/430	
<b>Warp/Weft</b>	ASTM D-751 (8 " x 10 ") Specimen	N	N	N	N	N	N	N	N	N
<b>Adhesion</b>	ASTM D-751 RF Weld	80N/50mm	85N/50mm	90N/50mm	90N/50mm	100N/50mm	100N/50mm	100N/50mm	100N/50mm	100N/50mm
<b>Temperature resistance</b>	DIN EN 1876-1 ASTM D-2136	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C
<b>Fire behaviour</b>	ISO 3795	B2	B2	B2	B2	B2	B2	B2	B2	B2
<b>Environmental Protective</b>	EU	REACH								
<b>Surface Treatment</b>	Acrylic/PVDF	NA	NA	NA	Acrylic	Acrylic	Acrylic	Acrylic	PVDF	
<b>Weather Protection</b>		Anti UV/Mildew	Anti UV/Mildew	Anti UV/Mildew	Anti UV/Mildew	Anti UV/Mildew	Anti UV/Mildew	Anti UV/Mildew	Anti UV/Mildew	Anti UV/Mildew
<b>Special Property</b>		Transluent	Transluent	Blockout	Transluent	Blockout	Blockout	Blockout	Blockout	Blockout
<b>Available Width</b>	Meter	1-5m	1-5m	1-5m	1-3.2m	1-3.2m	1-3.2m	1-3.2m	1-3.2m	1-3.2m

Leading China PVC Fabric Producer  
[www.chinatarps.com](http://www.chinatarps.com) [Manager@chinatarps.com](mailto:Manager@chinatarps.com) 0086-13757342702