



HUAWEI TECHNIAL TEXTILE

Technical Sheet

Warehouse	Product Code				
Total Weight	DIN EN ISO 2286-2 ASTM D-751. 10	650g/m2 19oz/sq. yd	750g/m2 22oz/sq. yd	850g/m2 25oz/sq. yd	950g/m2 28oz/sq. yd
Yarn	Denier	1000x1000D	1000x1000D	1000x1000D	1000x1000D
Yarn Count	Per Inch	23x23	23x23	23x23	30x30
Tensile Strength Warp/Weft	DIN EN ISO 1421/V1 ASTM D-751 B	2800/2700 N/50mm	2900/2800 N/50mm	3000/2800 N/50mm	3800/3500 N/50mm
Tear Strength Warp/Weft	DIN 53363 ASTM D-751 (8 “ x 10 “) Specimen	290/280 N	300/290 N	310/300 N	450/430 N
Adhesion	ASTM D-751 RF Weld	100N/50mm	100N/50mm	100N/50mm	100N/50mm
Temperature resistance	DIN EN 1876-1 ASTM D-2136	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C	-40° C/+70° C
Fire behaviour	ISO 3795				
Environmental Protective	EU				
Surface Treatment	Acrylic/PVDF	Acrylic	Acrylic	Acrylic	PVDF
Weather Protection		Anti UV/Mildew	Anti UV/Mildew	Anti UV/Mildew	Anti UV/Mildew
Special Property		Blockout	Blockout	Blockout	Blockout
Available Width	Meter	1-3.2m	1-3.2m	1-3.2m	1-3.2m

Leading China PVC Fabric Producer

www.chinatarps.com Manager@chinatarps.com 0086-13757342702